#### **Product Features and Benefits**

- Combination safety / solar control window film
- Micro-layered film designed for tear resistance
- Virtually clear film with heat rejection properties
- Helps protect from broken glass hazards
- Increase comfort and help reduce air conditioning costs
- Helps extend the life of furnishings by significantly reducing harmful UV rays

## **Applications**

- Bomb Blast Mitigation
- Building Envelope Protection
- Helping to Deter Break & Entry
- Safety Glazing
- Seismic Preparedness
- Spontaneous Glass Breakage

## **Performance Testing**

Method	Glass Substrate	Film Attachment	Rating					
Safety Glazing								
16 CFR 1201	1/4" annealed		Category 2, 400 ft-lbs					
ANSI Z97.1	74 annealed		Class A (Unlimited), 400 ft-lbs					
Impact Resistance								
ASTMs E1886 / E1996	1/4" tempered	IPA	Missile Level C					
Blast Mitigation			Blast Load	Rating				
GSA TS01-2003 / ASTM F1642	1/4" tempered	IPA	6 psi, 42 psi*msec	GSA Level 2 / ASTM "No Hazard"				
	1" double pane (annealed)	IPA	8 psi, 60 psi*msec	GSA Level 2 / ASTM "No Hazard"				

<sup>\*</sup>Glazing systems vary. Contact 3M for more information.

# Film Properties (nominal)

Film Thickness Film Construction Micro-layered Laminated Tensile Strength 24,000 psi (MD) /26,000 psi (TD) Break Strength 200 lbs/in (MD) /215 lbs/in (TD) Elongation at Break 104% (MD) /118% (TD) Yield Strength 16,000 psi (MD) Elongation at Yield 8% Modulus 600 kpsi Abrasion Resistance (ASTM D1044) 3% Δ Haze Peel Strength (ASTM D3330) 4.5 lb/in Flammability (ASTM E84) Class A Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%					
Tensile Strength 24,000 psi (MD) /26,000 psi (TD)  Break Strength 200 lbs/in (MD) /215 lbs/in (TD)  Elongation at Break 104% (MD) /118% (TD)  Yield Strength 16,000 psi (MD)  Elongation at Yield 8%  Modulus 600 kpsi  Abrasion Resistance (ASTM D1044) 3% Δ Haze  Peel Strength (ASTM D3330) 4.5 lb/in  Flammability (ASTM E84) Class A  Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%	Film Thickness	8 mils			
Break Strength 200 lbs/in (MD) /215 lbs/in (TD)  Elongation at Break 104% (MD) /118% (TD)  Yield Strength 16,000 psi (MD)  Elongation at Yield 8%  Modulus 600 kpsi  Abrasion Resistance (ASTM D1044) 3% Δ Haze  Peel Strength (ASTM D3330) 4.5 lb/in  Flammability (ASTM E84) Class A  Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%	Film Construction	Micro-layered Laminated			
Elongation at Break 104% (MD) /118% (TD) Yield Strength 16,000 psi (MD) Elongation at Yield 8% Modulus 600 kpsi Abrasion Resistance (ASTM D1044) 3% Δ Haze Peel Strength (ASTM D3330) 4.5 lb/in Flammability (ASTM E84) Class A Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%	Tensile Strength	24,000 psi (MD) /26,000 psi (TD)			
Yield Strength 16,000 psi (MD)  Elongation at Yield 8%  Modulus 600 kpsi  Abrasion Resistance (ASTM D1044) 3% Δ Haze  Peel Strength (ASTM D3330) 4.5 lb/in  Flammability (ASTM E84) Class A  Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%	Break Strength	200 lbs/in (M	MD) /215 lbs/in (TD)		
Elongation at Yield 8%  Modulus 600 kpsi  Abrasion Resistance (ASTM D1044) 3% Δ Haze  Peel Strength (ASTM D3330) 4.5 lb/in  Flammability (ASTM E84) Class A  Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%	Elongation at Break	D) /118% (TD)			
Modulus     600 kpsi       Abrasion Resistance (ASTM D1044)     3% Δ Haze       Peel Strength (ASTM D3330)     4.5 lb/in       Flammability (ASTM E84)     Class A       Graves Area Tear Resistance (ASTM D1004)     1,100 lbs%	Yield Strength	0 psi (MD)			
Abrasion Resistance (ASTM D1044) 3% ∆ Haze Peel Strength (ASTM D3330) 4.5 lb/in Flammability (ASTM E84) Class A Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%	Elongation at Yield		8%		
Peel Strength (ASTM D3330)   4.5 lb/in     Flammability (ASTM E84)   Class A     Graves Area Tear Resistance (ASTM D1004)   1,100 lbs%	Modulus	00 kpsi			
Flammability (ASTM E84) Class A Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%	Abrasion Resistance (	3% ∆ Haze			
Graves Area Tear Resistance (ASTM D1004) 1,100 lbs%	Peel Strength (	4.5 lb/in			
D1004) 1,100 lbs%	Flammabilit	Class A			
	Graves Area Tear Resi	1,100 lbs%			
Puncture-Propagation-Tear (ASTM D2582) 10 lbf	Puncture-Propagation-Tear (	10 lbf			

Puncture	185 lbf									
Solar Properties – film applied to 1/4" glass										
	1/4" Clear	1/4" Tint	<b>Dual Clear</b>	Dual	Tint					
VLT	68%	41%	61%	36%						
VLR-Int	8%	7%	12%	11%						
VLR-Ext	9%	6%	16%	9%						
SHGC	0.51	0.44	0.56	0.42						
TSER	49%	56%	44%	58%						
UV Block	99.9%	99.9%	99.9%	99.9	9%					
Glare ↓	23%	36%	14%	29%						
U-Value	1.01	1.01	0.48	0.48						
Solar Heat ↓	38%	31%	21%	19	%					

#### IMPORTANT NOTICE:

This product is **not approved** in the State of Florida for use as hurricane, windstorm, or impact protection from wind-borne debris from a hurricane or windstorm. In compliance with Florida Statute 553.842, this product may not be advertised, sold, offered, provided, distributed, or marketed in the State of Florida as hurricane, windstorm, or impact protection from wind-borne debris from a hurricane or windstorm.

The information provided in this report is believed to be reliable; however, due to the wide variety of intervening factors, 3M does not warrant that the results will necessarily be obtained. All details concerning product specifications and terms of sale are available from 3M



888.616.1488







## **Health and Safety**

When handling any chemical products, read the manufacturers' container labels and the Safety Data Sheets (SDS) for important health, safety and environmental information. To obtain SDS sheets for 3M products go to <u>3M.com/SDS</u>, or by mail or in case of an emergency, call 1-888-364-3557 or 1-651-737-6501. When using any equipment, always follow the manufacturers' instructions for safe operation.

### **Technical Information**

Technical information and data, recommendations, and other statements provided by 3M are based on information, tests, or experience which 3M believes to be reliable, but the accuracy or completeness of such information is not guaranteed. Such technical information and data are intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. The typical values shown should not be used for the purpose of specification limits. If you have questions about this Product, contact the Customer Service Department at 1-888-616-1488.

#### **Product Use**

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

## Warranty

3M warrants that each 3M product will be free from defects in material and manufacture for the length of the product warranty. 3M MAKES NO OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

### **Limited Remedy**

If a 3M product does not conform to this warranty, the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

### **No Extension of Warranty**

In the case of an approved warranty claim, the replacement Product will carry only the remaining term of the original warranty period.

#### **Limitation of Liability**

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted.

#### IMPORTANT NOTICE:

This product is **not approved** in the State of Florida for use as hurricane, windstorm, or impact protection from wind-borne debris from a hurricane or windstorm. In compliance with Florida Statute 553.842, this product may not be advertised, sold, offered, provided, distributed, or marketed in the State of Florida as hurricane, windstorm, or impact protection from wind-borne debris from a hurricane or windstorm.

The information provided in this report is believed to be reliable; however, due to the wide variety of intervening factors, 3M does not warrant that the results will necessarily be obtained. All details concerning product specifications and terms of sale are available from 3M



888.616.1488





