

Commercial Solutions Division

3M™ Neutral 35 Exterior Window Film

Solar Control Window Film

Product Bulletin

1. Product Description

3M™ Neutral 35 Exterior is a metallized solar control film for exterior application. It has a durable scratch resistant coating and a weather resistant acrylic adhesive.

2. Applications

3M™ Neutral 35 Exterior is intended for exterior application on flat glass substrates.

3. Typical Properties

These are indicative values for 3M™ Window Film products.

Product construction	
Material base	Metallized Polyester
Adhesive	Pressure sensitive acrylic
Protective liner	Siliconized PET

Typical Performance Properties according to EN 410										
Glass type	Film Type	Visible Light			Total Solar Energy Rejected	G Value (SHGC)	LSG (Light to solar gain)	UV Block	Heat Gain Reduction	Glare Reduction
		Reflected (interior)	Reflected (exterior)	Transmission						
Single Pane		%	%	%	%		%	%	%	
Clear	No Film	9	8	89	19	0.82	1.1	38	NA	NA
	Neutral 35 EX	13	17	40	50	0.50	0.8	99	40	55
Tinted	No Film	6	6	53	37	0.63	0.8	NA	NA	NA
	Neutral 35 EX	8	16	24	59	0.41	0.6	99	34	55
Double Pane										
Clear	No Film	15	15	79	30	0.70	1.1	NA	NA	NA
	Neutral 35 EX	18	19	36	62	0.39	0.9	99	45	54
Tinted	No Film	13	8	47	49	0.51	0.9	NA	NA	NA
	Neutral 35 EX	15	17	22	70	0.30	0.7	99	41	54

The values above are the results of illustrative lab test measurements and shall not be considered as a commitment from 3M.

4. User Information

4.1 Shelf Life & Storage (prior to application)

Shelf life is 5 years from the manufacturing date. Material should be stored in its original packaging, laying in a horizontal orientation, away from direct sunlight. Heavy objects should not be placed on top of it to avoid damaging the product. Recommended storage conditions are +21°C and 40 – 50% relative humidity. Avoid extreme temperature ranges in storage.

The shelf life as defined above remains an indicative and maximum data, subject to many external and non-controllable factors. It may never be interpreted as warranty.

4.2 Application

These are indicative values for 3M™ Window Film products.

Recommended substrate	Glass (as described in EN 15755-1)
Recommended surface	Flat to simple curved
Application method	Suitable for wet application
Application temperature	From +8°C to +45°C
Application guidelines	Check weather forecast when planning the application. Do not install during precipitation or if the exterior temperature should drop below 0°C within 15 days after installation.
Service temperature	From -40°C to +70°C
Edge sealing	Necessary on all edges
Drying Time	Final adhesion is reached after approximately 20 days at +18°C and dry conditions. Please refer to local instructions for details.

4.3 Maintenance and Cleaning

Use a cleaning agent designed for high quality glass surfaces. The cleaning agent must be wet and non-abrasive with a pH value between 6 and 8 (neither strongly acidic nor strongly alkaline).

5. Remarks

This bulletin provides technical information only.
To request additional product information see address below.

Important Notice

All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.
Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.



Responsible for this technical bulletin:

Commercial Solutions Division
Hermeslaan 7
1831 Diegem, Belgium
www.3mgraphics.com/eu

3M Deutschland GmbH
Carl-Schurz-Str. 1
41453 Neuss, Germany

3M is a trademark of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.



info@solartint.com

888.616.1488



info@st.graphics



solartint.com



st.graphics